


**Amendments to the Claims:**

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) Primer composition comprising a silane-terminated compound ~~A1~~ comprising isocyanate-reactive groups, derived from ~~for the preparation of~~ ~~which the following are used~~

- a polyisocyanate ~~A~~ which has at least three isocyanate groups;
- at least one silane ~~B~~ of the formula (I)



wherein ~~whereby~~ R<sup>1</sup> represents methyl or ethyl,


R<sup>2</sup> represents a C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>1</sup>,

R<sup>3</sup> represents H, a C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>1</sup>, and

X(1) a primary amino group or at least an organic residue carrying primary amino groups and;

- a cross-linking agent ~~C~~ having at least three isocyanate-reactive functional groups.

2. (Currently Amended) Primer composition according to claim 1, wherein ~~characterized in that~~ at least another silane ~~B~~ of the formula (I') is used for producing the silane-terminated compound ~~A1~~ comprising isocyanate-reactive groups



~~wherein whereby~~  $R^4$  represents methyl or ethyl,

$R^5$  ~~represents~~  $\text{a-H}$ , a  $\text{C}_1$ -to  $\text{C}_4$ -alkyl or  $\text{OR}^4$ ,

$R^6$  ~~represents~~  $\text{a-H}$ , a  $\text{C}_1$ -to  $\text{C}_4$ -alkyl or  $\text{OR}^4$ , and

$\text{X}(2)$  ~~represents~~ a primary amino or mercapto or hydroxylic group or an organic residue which carries at least a primary amino or mercapto or hydroxylic group.

3. (Currently Amended) Primer composition according to claim 2, wherein  
~~characterized in that~~  $R^6 = \text{OR}^4$  in formula (I)~~silane B~~, particularly  $R^6 = R^5 = \text{OR}^4$ .

4. (Currently Amended) Primer composition according to claim 2, wherein  
~~characterized in that~~  $R^4 = \text{methyl}$  in formula (I)~~silane B~~.

5. (Currently Amended) Primer composition according to claim 2, wherein  
~~characterized in that~~  $\text{X}(2) = \text{SH}$ ,  $\text{NH}_2$  or  $\text{OH}$ ,~~particularly SH, in silane B~~ formula (I).

6. (Currently Amended) Primer composition according to claim 1, wherein  
~~characterized in that~~ the primer composition is essentially free from isocyanate groups.

7. (Currently Amended) Primer composition according to claim 1, wherein  
~~characterized in that~~ the polyisocyanate ~~A~~ is a biuret or an isocyanurate of one or more diisocyanates or an adduct of polyisocyanate and polyol.

8. (Currently Amended) Primer composition according to claim 1, wherein  
~~characterized in that~~ the polyisocyanate ~~A~~ is an isocyanurate of an aliphatic diisocyanate,  
~~preferably an isocyanurate of hexamethylenediisocyanate.~~

9. (Currently Amended) Primer composition according to claim 1, wherein  
~~characterized in that~~  $R^3 = \text{OR}^1$ ,~~particularly~~  $R^3 = R^2 = \text{OR}^1$ ,~~in silane B~~ formula (I).

10. (Currently Amended) Primer composition according to claim 1, wherein  
~~characterized in that~~  $R^1 = \text{methyl}$  in ~~silane B~~ formula (I).

11. (Currently Amended) Primer composition according to claim 1, wherein  
~~characterized in that~~ ~~the they have~~ at least three isocyanate-reactive functional groups of the


cross-linking agent  $\text{C}$ , ~~all are identical or different from one another, preferably all are identical and are selected from SH, OH, NH or  $\text{NH}_2$ .~~

12. (Currently Amended) Primer composition according to claim 1, wherein ~~characterized in that~~ the cross-linking agent  $\text{C}$  is a polyol, ~~particularly a triol.~~

13. (Currently Amended) Primer composition according to claim 12, wherein ~~characterized in that~~ the cross-linking agent  $\text{C}$  has a OH-equivalent weight of 30 – 350 g/eq, ~~particularly 30 – 170 g/eq, preferably 30 – 65 g/eq.~~

14. (Currently Amended) Primer composition according to claim 1, wherein ~~characterized in that~~ the cross-linking agent  $\text{C}$  has a molecular weight of 90 – 100 g/mol, ~~particularly 90 – 1000 g/mol, preferably 120 – 150 g/mol.~~

15. (Currently Amended) Primer composition comprising a compound comprising isocyanate-reactive groups, derived from a reaction of  
- a product carrying isocyanate groups and formed from a reaction of polyisocyanate  
which has at least three isocyanate groups and at least a silane of the formula (I)



wherein  $\text{R}^1$  represents methyl or ethyl,

$\text{R}^2$  represents a  $\text{C}_1$ -to  $\text{C}_4$ -alkyl or  $\text{OR}^1$ ,


$\text{R}^3$  represents H, a  $\text{C}_1$ -to  $\text{C}_4$ -alkyl or  $\text{OR}^1$ , and


$\text{X(1)}$  represents a primary amino group or at least an organic residue carrying primary amino groups,

the reaction to form the product being conducted in a stoichiometric excess of isocyanate groups of the polyisocyanate with respect to the isocyanate-reactive groups of the silane of formula (I); and

\_\_\_\_\_ - a cross-linking agent having at least three isocyanate-reactive functional groups according to claim 1, characterized in that the compound **A1** is the reaction product of a cross-linking agent **C** and an intermediate product **AB** which is carrying isocyanate groups and which is previously formed from a polyisocyanate **A** and at least a silane **B** of the formula (I) in a stoichiometric excess of isocyanate groups of the polyisocyanate **A** with respect to the isocyanate-reactive groups of silane **B**.

16. (Currently Amended) Primer composition according to claim 1, wherein characterized in that the silane-terminated compound **A1** has the formula (VI) or (VII)





wherein ~~whereby~~ R" represents a divalent residue, particularly an aliphatic alkylene residue, preferably hexamethylene residue;

R<sup>4</sup> represents R<sup>1</sup>, methyl or ethyl;

R<sup>5</sup> represents R<sup>2</sup>, H, C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>4</sup>; and

R<sup>6</sup> represents R<sup>3</sup>, H, C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>4</sup>.

17. (Currently Amended) Primer composition according to claim 1, wherein the primer composition further includes ~~characterized in that in addition to the compound A1 a coupling agent, particularly a silicon-organic compound, preferably a trialkoxy silane, is also present.~~

18. (Currently Amended) Primer composition according to claim 17, wherein ~~characterized in that the coupling agent is a trialkoxy silane carrying primary amino groups, particularly a trimethoxy silane having primary amino groups or a trialkoxy silane having vinyl groups.~~


19. (Currently Amended) Primer composition according to claim 1, further comprising ~~characterized in that in addition to the compound A1 a catalyst, particularly a tin-organic catalyst, preferably selected from the group consisting of dibutyl tin dilaurate, dibutyl~~

~~tin dichloride, tin thioester complexes, mono n-butyl tin trichloride, di n-butyl tin oxide, di n-butyl tin diacetate and dibutyl tin carboxylate is also present.~~

20. (Currently Amended) Primer composition according to claim 1, further comprising ~~characterized in that in addition to the compound A1~~ a solvent which does not react with isocyanates at room temperature ~~and which is preferably selected from the group consisting of xylene, toluene, hexane, heptane, octane, acetone, methylethyl ketone, methylpropyl ketone, methylisopropyl ketone, methylbutyl ketone, diethyl ketone, diisopropyl ketone, methyl acetate, ethyl acetate, propyl acetate, butyl acetate, methoxy ethyl acetate, methoxy propyl acetate and 2 (2-methoxy ethoxy) ethyl acetate.~~

21. (Currently Amended) Primer composition according to claim 1, further comprising ~~characterized in that at least a filler, particularly carbon black is present.~~

22. (Currently Amended) Compound of formula



wherein whereby

R<sup>1</sup> represents methyl or ethyl;

R<sup>2</sup> represents a H, a C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>1</sup>;

R<sup>3</sup> represents a H, a C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>1</sup>;

R<sup>4</sup> represents a R<sup>1</sup>, methyl or ethyl;

$R^5$  represents a  $R^2$ , a H, a  $C_1$ -to  $C_4$ -alkyl or  $OR^4$ ;

$R^6$  represents a  $R^3$ , a H, a  $C_1$ -to  $C_4$ -alkyl or  $OR^4$ ;

R represents a polyisocyanate ~~A~~ after removing all the isocyanate groups;

$R'$  represents a cross-linking agent ~~C~~ after removing all the isocyanate-reactive groups;

$X^1$  represents a functional group which is produced from the reaction of an isocyanate-reactive group and an isocyanate, ~~particularly an urea, urethane or thiocarbamate group~~;

$X^2$  represents a functional group which is produced from a reaction of an isocyanate-reactive group and an isocyanate, ~~particularly an urea, urethane or thiocarbamate group~~;

$Y^1$  represents a functional group which is produced from the reaction of an isocyanate-reactive group and isocyanate, particularly an urea, urethane or thiocarbamate group;

Y represents an isocyanate-reactive group, ~~particularly  $NH_2$ , SH or OH~~;


n represents ~~the values~~ 3, 4, 5 or 6, ~~particularly 3 or 4~~;


q represents ~~the values~~ 3, 4, 5 or 6, ~~particularly 3 or 4~~;

p represents a value of from the values between 0 to and n-1; and

m represents ~~the values~~ 1, 2, 3 or 4, ~~particularly 1 or 2~~, selected in such a way that  $q - m \geq 2$ .

23. (Currently Amended) Compound according to claim 22, wherein characterized in  
~~that~~ the compound has the formula (VI) or (VII)





~~wherein~~ ~~whereby~~ R'' represents a divalent residue, particularly an aliphatic alkylene residue, preferably hexamethylene residue;

R<sup>4</sup> represents a R<sup>1</sup>, methyl or ethyl;

R<sup>5</sup> represents a R<sup>2</sup>, a H, a C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>4</sup>; and

R<sup>6</sup> represents a R<sup>3</sup>, a H, a C<sub>1</sub>-to C<sub>4</sub>-alkyl or OR<sup>4</sup>.

24. (Currently Amended) Method of using the primer composition according to claim 1 as a primer for adhesives, sealants or floorings, ~~particularly for 1-component moisture-curing polyurethane adhesives or sealants based on polyurethanes or polyurethane-silane hybrids.~~

25. (Currently Amended) Method comprising applying ~~characterized in that~~ a primer composition according to claim 1 ~~is applied~~ by means of brush, felt, cloth or sponge on a substrate manually or automatically or by means of robots.

26. (Currently Amended) Method according to claim 25, wherein ~~characterized in that~~ the substrate is glass or glass ceramics.

27. (New) The primer composition according to claim 1, wherein the cross-linking agent includes free isocyanate-reactive functional groups.



28. (New) The primer composition according to claim 1, wherein the primer composition comprises the silane-terminated compound in a solution free of water.